

ANCORE CHIMICE



117.257 CARTUS 280 ml + 1 MIXER STATIC
124764 CARTUS 165 ml + 1 MIXER STATIC

ACCESORII

117375 PACHET 5 MIXER STATIC
117431 5 DIBLURI 13x85 mm pentru suruburi M10,M12

Date tehnice :

Baza	Vinilester
Consistenta	Pasta stabila
Sistem de uscare	Uscare chimica
Timp de uscare	- 5 °C Start 90 min Final 360 min 0 °C Start 45 min Final 180 min 5 °C Start 25 min Final 120 min 10 °C Start 15 min Final 80 min 20 °C Start 6 min Final 45 min 30 °C Start 4 min Final 25 min 35 °C Start 2 min Final 20 min
Greutate specifica (DIN 53479)	Cca 1,65 g/cm ³
Rezistenta termica	+110°C
Rezistenta la arcuire maxima	37 N/mm ²
Rezistenta compresie maxima	103 N/mm ²
Modul de elasticitate dinamic	1200 N/mm ²

Descriere : Fixarea fara presare a suruburilor autofiletante, carligelor filetate, barelor de ramforsare in materiale solide sau in cele care au goluri interioare (caramizi) chiar si la margini. Poate fi folosit ca mortar de reparatii









Parametrii de aplicare si incarcare

Diametru surub	mm	M8	M10	M12	M16	M20
Diametru gaurire	mm	10	12	14	18	24
Adancime gaurire	mm	80	90	110	125	170
Distanta minima de margine	mm	40	50	60	70	90
Distanta minima radiala	mm	80	90	110	125	170
Moment de strangere	Nm	10	20	40	60	120
Rezistenta la tractiune (beton)	kN	6,6	9,9	14	15,7	26,3
Rezistenta la forfecare (beton)	kN	7,9	12,6	18,3	34,6	54

Aplicatii :

- Instalarea « mainilor curente » pentru scari, antenelor, parasolarelor, jaluzelelor exterioare, boilerelor, rafturilor, aparatelor de aer conditionat, echipamentelor sanitare (chiuvete, vase toaleta), suportilor de TV etc.

Instructiuni de folosire :

	1. Gauriti folosind o masina cu percutie		5. Infiletati fara a forta surubul pana la capat
	2. Curatati gaura (periatii: 4x, spalati: 4x, periatii: 4x)		6. Controlati vizual daca mortarul a iesit afara
	3. Taiati varful mixerului aproximativ 10 cm		7. Observati timpul de uscare
	4. Incepand de la capat umpleti gaura cu mortar		8. Instalati aplicatia si piulita

Proprietati:

- ancore chimice de inalta calitate
- rezistenta chimica ridicata, proprietati mecanice ridicate
- potrivite pentru suprafete umede, se usuca sub apa
- fara crapaturi dupa uscare

Ambalaj : Cartuse 280 ml ; 165 ml

SOUDAL

Reprezentanta SOUDAL NV Belgia
Sos BUCURESTI TARGOVISTE NR 697C
CREVEDIA JUD DAMBOVITA
Tel/Fax 021 3515804 ; office@soudal.ro



Utilizare :

Metoda : pistol de silicon

Temperatura de aplicare : -5°C....

Termen de garantie si depozitare :

- 18 luni in ambalajul original
- depozitare in spatii reci si uscate la temperaturi de +5°C....+25°C

Certificate de calitate:



Produs de SOUDAL NV in Turnhout (Belgia) in conformitate cu standardul de calitate ISO 9001, 2000

Masuri de protectie :

- aplicati masurile uzuale de igiena
- consultati eticheta pentru mai multe detalii